



PT451 | 4290-4293 **Poli-Flex® Glossy**

100% Polyurethane
Roll Length: 25m x Roll Width: 0,5m

Poli-Flex

GLOSSY BLACK GLOSSY GOLD GLOSSY RED GLOSSY WHITE

Technical data - Transfer film: Polyurethane, cast/Adhesive: polyurethane-hotmelt/Thickness [mm]: 0.10 +/- 10%/Liner: PET film, self-adhesive | Transfer conditions - Temperature: 160°C/Pressure: 3.5 bar [medium pressure]/Time: 15 sec. | Wash resistance: 80°C/Suitable for tumble drying and dry-cleaning; Perchloroethylene (Tetrachloroethylene)/Wash textile inside out | POLI-FLEX® GLOSSY is a high-quality, ecologically proven polyurethane film with a high-gloss surface. | POLI-FLEX® GLOSSY is suitable to transfer onto textiles like cotton, mixtures of polyester/cotton and polyester/acrylic | Suitable for lettering on T-shirts, jerseys, sports and leisure wear, sports bags and fan articles such as flags and pennants. | POLI-FLEX® GLOSSY can be cut with all current plotters. We recommend using a standard blade (45°). Once it has been weeded, the cut flex film is transferred using a transfer press. The PET liner should be removed warm. | Nylon and textiles with hydrophobic impregnation are not suitable for heat transfer. In this case, L-Flex Nylon T500 should be used. | POLI-FLEX® GLOSSY is covered with a self-adhesive PET liner, enabling repositioning of the plotted motifs. POLI-FLEX® GLOSSY has excellent opacity. | If the specified temperature and pressure requirements are not met during the heat transfer printing process, secure and permanent adhesion of the flex film cannot be guaranteed. | We recommend carrying out an application test on original materials. | Due to the various influences resulting from the production and transfer of the transfer film, the nature of the materials and the washing and cleaning conditions, product liability can only apply to unprocessed materials.